



CENTURY COLORANT PRODUCT INFORMATION SHEET

Product Code 70-0150

Name Red Oxide

Description

Century Colorants are made with Liprol Polyol. This polyol has a hydroxyl value of 260 and a low viscosity. These important properties make it ideal to achieve solvent free, low viscosity concentrates that are suitable for machine dispensing. The high pigment loading enable low dosing in finished products and high quality lightfast pigments are used.

This yields reactive urethane products with unique features like high crosslinking densities, high loadings, high adhesion and the formulating flexibility of very low viscosity.

Solids %	100
Solvent %	0
Pigment Manufacturer	Nubifer
Pigment Name / Shade #	R-5531 / PR 101
Renewable Content %	43
Wt/Wt % Pigment	56
Specific Gravity	1.207
Equivalent Weight	419
Molecular Weight	465
Shore Hardness A/D	90/75

This information is furnished without warranty, express or implied, except that it is accurate to the best knowledge of Consolidated Biofuels Corporation. It relates only to the specific material design designated herein, and does not relate to use in combination with any other material or any process. Consolidated Biofuels Corporation assumes no legal responsibility for use or reliance upon this information.

Meadow Polymers a Division of Consolidated Biofuels Corp. 7651 Vantage Way, Delta, BC, V4G 1A6 Canada