



PRODUCT DATA SHEET

Product Code 2-70-P350

Name Liprol P 350

Description

The "P" refers to our P series of polyols in which we have developed a novel process in which the great majority of OH groups are in a primary position. This makes them more available for quick reactions and faster response times to catalysts.

Renewable %	>80
Solids %	100
Specific Gravity	0.964
Viscosity (cps)	800-900
Hydroxyl Value	350-360
Equivalent Weight	158
Water	< 250 ppm
Cloud Point	~ 0 Celsius

The recommended temperature range for storage is 10 -30 C.

The products should be protected from atmospheric oxygen.

The practical shelf life of Liprol is 6 months.

A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months can not be given by Consolidated Biofuels.

This information is furnished without warranty, express or implied, except that it is accurate to the best knowledge of Consolidated Biofuels Ltd. It relates only to the specific material design herein, and does not relate to use in combination with any other material or any process. Consolidated Biofuels Ltd assumes no legal responsibility for use or reliance upon this information.

Meadow Polymers a Division of Consolidated Biofuels Ltd. 7651 Vantage Way, Delta, BC, V4G 1A6 Canada